

ONYX® 1" High Temperature, Standard Magnetics

US Specifications

Construction


Anode	304 Stainless Steel
Cathode Body	OFHC Copper
Insulator	Ceramic

Cooling Requirements

Flow Rate at Maximum Power	0.25 GPM
Maximum Input Pressure, Open Drain	60 psi
Maximum Input Temperature	68 °F

Dimensions

A	Consult Factory
B	Consult Factory
C	0.750"



General

Magnetic Enhancement	Permanent (NdFeB) Encapsulated
Maximum Temperature	392 °F
Source to Substrate Distance	2.000" - 12.000"
Weight, Approximate Without Options	Consult Factory

Maximum Sputtering Power *

Cathode Voltage	100 - 1000 Volts
Discharge Current	0.1 - 1 Amps
Indirect Cooled Mode, DC	75 Watts
Indirect Cooled Mode, RF	25 Watts
Operating Pressure	2 - 50 mTorr

Mounting, Standard

Power Cable, DC	RG142
Power Cable, RF	RG142
Power Connector, DC	Type N Connector, External Threads
Power Connector, RF	Type N Connector, External Threads
Stem, Outer Dimension Tubing	0.750"
Water, Outer Dimension Tubing	0.187"

Target

Cooling	Indirect
Diameter	1.000"
Form	Circular / Planar
Thickness	0.010" - 0.0625"

Specifications Disclaimer

- All Angstrom Sciences NdFeB magnets are totally encapsulated and protected from degradation by water.
 - All sources are available in external configurations.
 - * Maximum power for cathode only, a target material's properties, such as, thermal and electrical conductivity may limit the maximum process power level.
 - Some custom-engineered and specialty magnetrons may not meet standard specifications.
 - Specifications are subject to change without notice.
 - Typical performance. Results may vary with process parameters such as pressure, flow rate, target material, and substrate rotation, etc.
-

Please contact us for specifications regarding your application.

Angstrom Sciences | Call +1-412-469-8466 | www.angstromsciences.com