

# **ONYX® 3" IC Target, Standard Magnetics**

# Metric Specifications

	meane openingations					
C	onstruction					
	Anode		304 Stainless Steel			
	Cathode Body		OFHC Copper			
	Insulator		CTFE			
C	ooling Requireme	ents				
	Flow Rate at Maximum Power		0.05 LPS			
	Maximum Input Pressure, Open Drain		4 BAR			
	Maximum Input Temperature		20 °C			
D	imensions					
	A	96.9 mm	⊬——B—	<b>─</b> →		
	В	63.5 mm				
	С	19.1 mm	Ţ			
			1 )			

# General

Magnetic Enhancement	Permanent (NdFeB) Encapsulated
Maximum Temperature	100 °C
Source to Substrate Distance	50.8 mm - 304.8 mm
Weight, Approximate Without Options	1.9 kg

# Maximum Sputtering Power \*

Cathode Voltage	100 - 1500 Volts
Discharge Current	0.1 - 3 Amps
Indirect Cooled Mode, DC	1.5 kW
Indirect Cooled Mode, RF	700 Watts
Operating Pressure	0.5 - 50 mTorr

# Mounting, Standard

Power Cable, DC	1675A
Power Cable, RF	1675A
Power Connector, DC	Type N Connector, External Threads
Power Connector, RF	Type HN Connector, External Threads
Stem, Outer Dimension Tubing	19.1 mm
Water, Outer Dimension Tubing	6.4 mm

# Target

Cooling	Indirect
Diameter	76.2 mm
Form	Circular / Planar
Thickness	0.3 mm - 9.6 mm

# Specifications Disclaimer

- All Angstrom Sciences NdFeB magnets are totally encapsulated and protected from degradation by water.
- All sources are available in external configurations.
- \* Maximum power for cathode only, a target material's properties, such as, thermal and electrical conductivity may limit the maximum process power level.
- Some custom-engineered and specialty magnetrons may not meet standard specifications.
- · Specifications are subject to change without notice.
- Typical performance. Results may vary with process parameters such as pressure, flow rate, target material, and substrate rotation, etc.

Please contact us for specifications regarding your application.

Angstrom Sciences | Call +1-412-469-8466 | www.angstromsciences.com